

Tipco Tipcolene® PPH-OIT - Unfilled Polypropylene Homopolymer Compound with Copper Inhibitor (Metal Deactivator)

Category : Polymer , Thermoplastic , Polypropylene (PP)

Material Notes:

PP Homopolymer with Copper Inhibitor (Metal De-activator) Applications: Automotives & Electrical Processing: Injection

Molding Information provided by the Manufacturer, Tipco Industries Ltd., India.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Tipco-Tipcolene-PPH-OIT-Unfilled-Polypropylene-Homopolymer-Compound-with-Copper-Inhibitor-Metal-Deactivator.php

Physical Properties	Metric	English	Comments
Density	0.920 g/cc	0.0332 lb/in ³	ASTM D792
Linear Mold Shrinkage	0.019 cm/cm	0.019 in/in	ASTM D955
Melt Flow	8.0 g/10 min	8.0 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	35.0 MPa	5080 psi	ASTM D638
Elongation at Break	>= 50 %	>= 50 %	ASTM D638
Flexural Yield Strength	34.0 MPa	4930 psi	ASTM D790
Izod Impact, Notched (ISO)	5.00 kJ/m ²	2.38 ft-lb/in ²	ASTM D256

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China