

Tipco Tipcolite® TMHS 291 Phenolic Compound, Khaki Cotton Fabric, in fluffy form, Soft Flow & High Impact Strength

Category : Polymer , Thermoset , Phenolic

Material Notes:

Soft Flow Phenolic Compound, Reinforced with Khakhi Cotton Fabric, in fluffy form
Applications: Defence Applications
Processing: Compression Molding
Information provided by the Manufacturer, Tipco Industries Ltd., India.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Tipco-Tipcolite-TMHS-291-Phenolic-Compound-Khaki-Cotton-Fabric-in-fluffy-form-Soft-Flow-High-Impact-Strength.php

Physical Properties	Metric	English	Comments
Density	1.43 g/cc	0.0517 lb/in ³	ASTM D792
Apparent Bulk Density	0.200 g/cc	0.00723 lb/in ³	TRM-37
Linear Mold Shrinkage	0.0040 cm/cm	0.0040 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	50.0 MPa	7250 psi	ASTM D638
Flexural Yield Strength	82.0 MPa	11900 psi	ASTM D790
Izod Impact, Unnotched (ISO)	20.0 kJ/m ²	9.52 ft-lb/in ²	ASTM D256

Electrical Properties	Metric	English	Comments
Volume Resistivity	3.16e+9 ohm-cm	3.16e+9 ohm-cm	ASTM D257
Surface Resistance	3.16e+8 ohm	3.16e+8 ohm	ASTM D257
Dielectric Strength	3.20 kV/mm	81.3 kV/in	ASTM D149

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China