

## Tisan TISOPLen® 10% Calcite Filled Heat Stabilized Homopolymer Polypropylene

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 10% Calcium Carbonate (CaCO<sub>3</sub>) Filler

### Material Notes:

TISOPLen has a wide area of application in furniture, durable goods, household appliances, electrics/electronics, and telecommunication industries. General specifications include Low density, Low moisture intake, High impact resistance, Excellent chemical resistance, Electrical isolation, High performance/affordable price, Easy processability. Mineral filled TISOPLen compounds have a long lasting thermal-dimensional stability, increased mechanical and hardness characteristics, decreased mold shrinkage and improved surface appearance. Glass fiber reinforcement will impart high tensile strength and impact resistance and yield improvements in thermal characteristics of TISOPLen products. Excellent resistance to weak acids, weak alkalis, and strong alkalis. Good resistance to strong acids and alcohols. Medium resistance to hydrocarbons and engine fuels. Weak resistance to organic solvents.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Tisan-TISOPLen-10-Calcite-Filled-Heat-Stabilized-Homopolymer-Polypropylene.php](http://www.lookpolymers.com/polymer_Tisan-TISOPLen-10-Calcite-Filled-Heat-Stabilized-Homopolymer-Polypropylene.php)

Physical Properties	Metric	English	Comments
Density	0.970 g/cc	0.0350 lb/in <sup>3</sup>	ISO 1183
Linear Mold Shrinkage	0.014 cm/cm	0.014 in/in	
Melt Flow	19 g/10 min	19 g/10 min	ISO 1133
Ash	10 %	10 %	ISO 3451

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	65	65	ISO 868
Tensile Strength at Break	19.0 MPa	2760 psi	ISO 527-2
Tensile Strength, Yield	24.0 MPa	3480 psi	ISO 527-2
Elongation at Break	6.0 %	6.0 %	ISO 527-2
Elongation at Yield	7.0 %	7.0 %	ISO 527-2
Modulus of Elasticity	1.40 GPa	203 ksi	ISO 527-2
Izod Impact, Notched (ISO)	3.50 kJ/m <sup>2</sup>	1.67 ft-lb/in <sup>2</sup>	ISO 180

Thermal Properties	Metric	English	Comments
Melting Point	165 °C	329 °F	
Vicat Softening Point	115 °C	239 °F	ISO 306
Heat Distortion Temperature	105 °C	221 °F	ISO 75-2

Thermal Properties	Metric	English	Comments
--------------------	--------	---------	----------

Electrical Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Comparative Tracking Index	600 V	600 V	TS EN 60112
----------------------------	-------	-------	-------------

Processing Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Feed Temperature	70.0 °C	158 °F	
------------------	---------	--------	--

Rear Barrel Temperature	190 - 210 °C	374 - 410 °F	Aft-1. Region Temperature
-------------------------	--------------	--------------	---------------------------

Middle Barrel Temperature	190 - 210 °C	374 - 410 °F	Mid-2. Region Temperature
---------------------------	--------------	--------------	---------------------------

Front Barrel Temperature	190 - 210 °C	374 - 410 °F	Pre-3. Region Temperature
--------------------------	--------------	--------------	---------------------------

Nozzle Temperature	200 °C	392 °F	
--------------------	--------	--------	--

Melt Temperature	170 - 190 °C	338 - 374 °F	
------------------	--------------	--------------	--

Drying Temperature	80.0 °C	176 °F	Predrying Temperature
--------------------	---------	--------	-----------------------

Dry Time	1 hour	1 hour	Predrying Time
----------	--------	--------	----------------

Moisture Content	0.010 %	0.010 %	ISO 62
------------------	---------	---------	--------

Descriptive Properties	Value	Comments
------------------------	-------	----------

Block Temperature	45°C	
-------------------	------	--

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China