

Tisan TISOPLen® Flame Retardant (V0). Heat Stabilized, Copolymer Polypropylene

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene, Flame Retardant

Material Notes:

TISOPLen has a wide area of application in furniture, durable goods, household appliances, electrics/electronics, and telecommunication industries. General specifications include Low density, Low moisture intake, High impact resistance, Excellent chemical resistance, Electrical isolation, High performance/affordable price, Easy processability. Mineral filled TISOPLen compounds have a long lasting thermal-dimensional stability, increased mechanical and hardness characteristics, decreased mold shrinkage and improved surface appearance. Glass fiber reinforcement will impart high tensile strength and impact resistance and yield improvements in thermal characteristics of TISOPLen products. Excellent resistance to weak acids, weak alkalis, and strong alkalis. Good resistance to strong acids and alcohols. Medium resistance to hydrocarbons and engine fuels. Weak resistance to organic solvents.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Tisan-TISOPLen-Flame-Retardant-V0-Heat-Stabilized-Copolymer-Polypropylene.php

Physical Properties	Metric	English	Comments
Density	1.01 g/cc	0.0365 lb/in ³	ISO 1183
Linear Mold Shrinkage	0.017 cm/cm	0.017 in/in	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	68	68	ISO 868
Tensile Strength at Break	26.0 MPa	3770 psi	ISO 527-2
Tensile Strength, Yield	25.0 MPa	3630 psi	ISO 527-2
Elongation at Break	40 %	40 %	ISO 527-2
Elongation at Yield	39 %	39 %	ISO 527-2
Modulus of Elasticity	1.50 GPa	218 ksi	ISO 527-2
Izod Impact, Notched (ISO)	17.0 kJ/m ²	8.09 ft-lb/in ²	ISO 180

Thermal Properties	Metric	English	Comments
Melting Point	160 °C	320 °F	
Vicat Softening Point	150 °C	302 °F	ISO 306
Heat Distortion Temperature	120 °C	248 °F	ISO 75-2
Flammability, UL94	V-0	V-0	

Electrical Properties	Metric	English	Comments
Comparative Tracking Index	350 V	350 V	TS EN 60112

Processing Properties	Metric	English	Comments
Feed Temperature	70.0 °C	158 °F	
Rear Barrel Temperature	190 - 210 °C	374 - 410 °F	Aft-1. Region Temperature
Middle Barrel Temperature	190 - 210 °C	374 - 410 °F	Mid-2. Region Temperature
Front Barrel Temperature	190 - 210 °C	374 - 410 °F	Pre-3. Region Temperature
Nozzle Temperature	200 °C	392 °F	
Melt Temperature	170 - 190 °C	338 - 374 °F	
Drying Temperature	80.0 °C	176 °F	Predrying Temperature
Dry Time	1 hour	1 hour	Predrying Time
Moisture Content	0.20 %	0.20 %	ISO 62

Descriptive Properties	Value	Comments
Block Temperature	45°C	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China