

Toho Tenax Besfight® MC Type II (12,000 Filament) Nickel Coated Carbon Fiber

Category : Carbon , Carbon Fiber , Other Engineering Material , Composite Fibers

Material Notes:

Besfight MC Polyacrylonitrile (PAN) based fiber combines the mechanical properties and flexibility of carbon fiber with the electrical conductivity of nickel. It does not delaminate even at the mechanical breaking point due to the good bond between the carbon fiber and nickel. Used in thermoplastic compounds for EMI shielding. Information provided by Toho Carbon Fibers, a wholly owned subsidiary of Toho Tenax Co., Ltd.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Toho-Tenax-Besfight-MC-Type-II-12000-Filament-Nickel-Coated-Carbon-Fiber.php

Physical Properties	Metric	English	Comments
Density	3.40 g/cc	0.123 lb/in ³	
Thickness	0.500 microns	0.0197 mil	Ni Coating Thickness
Fiber Count	20800 dtex	18700 denier	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	3090 MPa	448000 psi	
Elongation at Break	1.5 %	1.5 %	
Tensile Modulus	216 GPa	31300 ksi	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	0.0000350 ohm-cm	0.0000350 ohm-cm	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China