

Total EVA 1005 VN 5 Ethylene Vinyl Acetate Copolymer - Blown Film

Category : Polymer , Film , Thermoplastic , Ethylene Vinyl Acetate , Ethylene Vinyl Acetate Copolymer (EVA), Film Grade

Material Notes:

EVA 1005 VN 5 is made by a high pressure tubular process. Grade for films with high transparency and good mechanical properties.

Contains an antioxidant. Application examples: Coextrusion, stretch film, paper stationary, geomembrane, stretch hood. Information provided by Total Petrochemicals.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Total-EVA-1005-VN-5-Ethylene-Vinyl-Acetate-Copolymer-Blown-Film.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.940 g/cc	0.940 g/cc	ISO 1183
Vinyl Acetate Content	17 %	17 %	
Thickness	40.0 microns	1.57 mil	for samples tested on this data sheet
	25.0 - 300 microns	0.984 - 11.8 mil	possible range, depending on extrusion conditions
Melt Flow	0.75 g/10 min @Load 2.16 kg, Temperature 190 °C	0.75 g/10 min @Load 4.76 lb, Temperature 374 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Film Tensile Strength at Yield, MD	6.30 MPa	914 psi	ISO 527-3
Film Tensile Strength at Yield, TD	4.50 MPa	653 psi	ISO 527-3
Film Elongation at Break, MD	320 %	320 %	ISO 527-3
Film Elongation at Break, TD	660 %	660 %	ISO 527-3
Modulus of Elasticity	0.0560 GPa	8.12 ksi	ISO 527-2
Elmendorf Tear Strength, MD	1.80 g/micron	45.7 g/mil	ISO 6383-2
Elmendorf Tear Strength, TD	4.10 g/micron	104 g/mil	ISO 6383-2
Dart Drop Test	680 g	1.50 lb	ISO 7765-1
Film Tensile Strength at Break, MD	38.0 MPa	5510 psi	ISO 527-3
Film Tensile Strength at Break, TD	39.0 MPa	5660 psi	ISO 527-3

Thermal Properties	Metric	English	Comments
Melting Point	89.0 °C	192 °F	ISO 11357

Thermal Properties	Metric	English	Comments
Optical Properties	Metric	English	Comments
Haze	2.0 %	2.0 %	ISO 14782
Processing Properties	Metric	English	Comments
Processing Temperature	150 - 180 °C	302 - 356 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China