

Total Finathene® LL 6010 FE 18P LLDPE film (discontinued **)

Category : Polymer , Film , Thermoplastic , Polyethylene (PE) , LLDPE , Linear Low Density Polyethylene (LLDPE), Blow Molding Grade

Material Notes:

Linear low density polyethylene made by gas phase process for blown film applications. Advised temperature profile: 190 to 220°C. Information provided provided by Total Petrochemicals. Total Petrochemicals includes former Fina and Atofina plastics product lines.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Total-Finathene-LL-6010-FE-18P-LLDPE-film-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	0.918 g/cc	0.0332 lb/in ³	on fluff; ISO 1183
Thickness	25.0 microns	0.984 mil	
Melt Flow	1.0 g/10 min @Load 2.16 kg	1.0 g/10 min @Load 4.76 lb	ISO 1133

Mechanical Properties	Metric	English	Comments
Film Tensile Strength at Yield, MD	11.0 MPa	1600 psi	ISO 527
Film Tensile Strength at Yield, TD	11.0 MPa	1600 psi	ISO 527
Film Elongation at Break, MD	600 %	600 %	ISO 527
Film Elongation at Break, TD	750 %	750 %	ISO 527
Secant Modulus, MD	0.180 GPa	26.1 ksi	ISO 5527
Secant Modulus, TD	0.200 GPa	29.0 ksi	ISO 5527
Dart Drop Test	170 g	0.375 lb	25µ; ISO 7765-1
Film Tensile Strength at Break, MD	45.0 MPa	6530 psi	ISO 527
Film Tensile Strength at Break, TD	40.0 MPa	5800 psi	ISO 527

Thermal Properties	Metric	English	Comments
Melting Point	124 °C	255 °F	ISO 11357-3

Optical Properties	Metric	English	Comments
Haze	11 %	11 %	25µ; ASTM D 1003

Descriptive Properties	Value	Comments
------------------------	-------	----------

Descriptive Properties

Value This material conforms to both European and American Food contact regulations.

Comments

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China