

## **Total HDPE 53090 High Density Polyethylene - Blow Molding**

Category: Polymer, Thermoplastic, Polyethylene (PE), HDPE, High Density Polyethylene (HDPE), Blow Molding Grade

## **Material Notes:**

HDPE 53090 is a semi high molecular weight (SHMW) high density polyethylene with high resistance to impact, rigidity and good Environmental Stress Crack Resistance. It has been specifically designed for the manufacture of blow molded articles (open top drums and jerry-cans) dedicated for the transportation of dangerous goods. HDPE 51090 is a pellet grade and contains antioxidants. Information provided by Total Petrochemicals.

## Order this product through the following link:

http://www.lookpolymers.com/polymer\_Total-HDPE-53090-High-Density-Polyethylene-Blow-Molding.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.953 g/cc	0.953 g/cc	ISO 1183
Environmental Stress Crack Resistance	10 hour	10 hour	FNCT; ISO 16770
Melt Flow	9.0 g/10 min	9.0 g/10 min	ISO 1133/G
	@Load 21.6 kg, Temperature 190 °C	@Load 47.6 lb, Temperature 374 °F	

Mechanical Properties	Metric	English	Comments
Charpy Impact, Notched	2.00 J/cm <sup>2</sup>	9.52 ft-lb/in <sup>2</sup>	ISO 179-1
	@Temperature -30.0 °C	@Temperature -22.0 °F	

Processing Properties	Metric	English	Comments
Processing Temperature	180 - 220 °C	356 - 428 °F	

## Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China