

Total Lacqtene® 2001 PBK 44 HDPE pipe (discontinued **)

Category : Polymer , Thermoplastic , Polyethylene (PE) , HDPE , High Density Polyethylene (HDPE), Pipe Grade

Material Notes:

LACQTENE® 2001 PBK 44 is a high density polyethylene produced by the gas phase polymerization process with hexene as comonomer.

LACQTENE® 2001 PBK 44 is a black compound especially developed for sewage pipe. LACQTENE® 2001 PBK 44 is best processed between 190 and 230°C. Information provided provided by Total Petrochemicals. Total Petrochemicals includes former Fina and Atofina plastics product lines.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Total-Lacqtene-2001-PBK-44-HDPE-pipe-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	0.954 g/cc	0.0345 lb/in ³	ISO 1183
Oxidative Induction Time (OIT)	>= 20 min	>= 20 min	200°C; EN 728
Carbon Black Loading	2.25 %	2.25 %	
Melt Flow	0.10 g/10 min	0.10 g/10 min	ISO 1133
	@Load 2.16 kg	@Load 4.76 lb	
	0.50 g/10 min	0.50 g/10 min	ISO 1133
	@Load 5.00 kg	@Load 11.0 lb	
High Load Melt Index	12 g/10 min	12 g/10 min	ISO 1133
	@Load 21.6 kg	@Load 47.6 lb	

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	59	59	ISO 868
Tensile Strength, Yield	24.0 MPa	3480 psi	ISO 527-2
Elongation at Break	>= 700 %	>= 700 %	ISO 527-2
Flexural Modulus	1.00 GPa	145 ksi	ISO 178
Izod Impact, Notched (ISO)	20.0 kJ/m ²	9.52 ft-lb/in ²	ISO 180
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
Melting Point	129 °C	264 °F	ISO 3146
Vicat Softening Point	120 °C	248 °F	ISO 306

Descriptive Properties	Value	Comments
Food Status	This material conforms to both European and American Food contact regulations.	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China