

Total Lumicene® mPE M 2710 EP Metallocene Polyethylene, Blown Film

Category : Polymer , Film , Thermoplastic , Polyethylene (PE) , LLDPE , Linear Low Density Polyethylene (LLDPE)/Hexene, Film Grade

Material Notes:

Lumicene® mPE M 2710 EP is a second generation metallocene based Low Density Polyethylene with hexene as comonomer. Lumicene® mPE M 2710 EP can be processed at high output rates with low extrusion pressure, excellent bubble stability and gauge control in comparison with conventional LLDPE and first generation metallocene based polyethylene. The combination of these features brings a significant downgauging potential. Lumicene® mPE M 2710 EP is especially dedicated to film applications where high gloss and high transparency are required, particularly in blend and coextrusion with LLDPE or LDPE. Lumicene® mPE M 2710 EP is suited for many applications in the field of consumer, industrial, food or hygiene packaging such as bags, deep freeze, collation shrink and lamination. Information provided by Total Petrochemicals.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Total-Lumicene-mPE-M-2710-EP-Metallocene-Polyethylene-Blown-Film.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.927 g/cc	0.927 g/cc	ISO 1183
Thickness	40.0 microns	1.57 mil	
Melt Flow	0.90 g/10 min @Load 2.16 kg, Temperature 190 °C	0.90 g/10 min @Load 4.76 lb, Temperature 374 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Film Tensile Strength at Yield, MD	13.5 MPa	1960 psi	ISO 527-3
Film Tensile Strength at Yield, TD	14.0 MPa	2030 psi	ISO 527-3
Film Elongation at Break, MD	650 %	650 %	ISO 527-3
Film Elongation at Break, TD	720 %	720 %	ISO 527-3
Elmendorf Tear Strength, MD	6.10 g/micron	155 g/mil	ISO 6383-2
Elmendorf Tear Strength, TD	16.3 g/micron	414 g/mil	ISO 6383-2
Dart Drop Test	200 g	0.441 lb	ISO 7765-1
Film Tensile Strength at Break, MD	51.0 MPa	7400 psi	ISO 527-3
Film Tensile Strength at Break, TD	48.0 MPa	6960 psi	ISO 527-3

Thermal Properties	Metric	English	Comments
Melting Point	119 °C	246 °F	ISO 11357

Vicat Softening Point Thermal Properties	118 °C Metric	244 °F English	ISO 306 Comments
---	------------------	-------------------	---------------------

Optical Properties	Metric	English	Comments
Haze	6.5 %	6.5 %	ISO 14782
Gloss	70 %	70 %	at 45°; ASTM D2457

Processing Properties	Metric	English	Comments
Processing Temperature	180 - 230 °C	356 - 446 °F	Blow Molding
Melt Temperature	200 °C	392 °F	Extrusion
Die Opening	0.0800 - 0.280 cm	0.0315 - 0.110 in	
Blow-up Ratio (BUR)	1.5 - 4.5	1.5 - 4.5	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China