

Total PPC 4660 Polypropylene, Heterophasic Copolymer

Category : Polymer , Thermoplastic , Polypropylene (PP)

Material Notes:

ATOFINA Polypropylene PPC 4660 is heterophasic copolymer.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Total-PPC-4660-Polypropylene-Heterophasic-Copolymer.php

Physical Properties	Metric	English	Comments
Bulk Density	0.525 g/cc	0.0190 lb/in ³	ISO 1183
Density	0.905 g/cc	0.0327 lb/in ³	ISO 1183
Melt Flow	3.5 g/10 min	3.5 g/10 min	ISO 1133
	@Load 2.16 kg, Temperature 230 °C	@Load 4.76 lb, Temperature 446 °F	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	82	82	ISO 2039-2
Tensile Strength, Yield	25.0 MPa	3630 psi	ISO 527-2
Elongation at Yield	7.0 %	7.0 %	ISO 527-2
Tensile Modulus	1.10 GPa	160 ksi	ISO 527-2
Flexural Modulus	1.20 GPa	174 ksi	ISO 527-2
Izod Impact, Notched (ISO)	18.0 kJ/m ²	8.57 ft-lb/in ²	ISO 179
	5.50 kJ/m ²	2.62 ft-lb/in ²	ISO 179
	@Temperature -20.0 °C	@Temperature -4.00 °F	
Charpy Impact, Notched	2.00 J/cm ²	9.52 ft-lb/in ²	ISO 179
	0.700 J/cm ²	3.33 ft-lb/in ²	ISO 179
	@Temperature -20.0 °C	@Temperature -4.00 °F	

Thermal Properties	Metric	English	Comments
Melting Point	165 °C	329 °F	ISO 3146
Deflection Temperature at 0.46 MPa (66 psi)	92.0 °C	198 °F	120°C per hour; ISO 75-2
Deflection Temperature at 1.8 MPa (264 psi)	50.0 °C	122 °F	120°C per hour; ISO 75-2
Vicat Softening Point			50N-50°C per hour; ISO 306

Thermal Properties	65.0 °C Metric	149 °F English	Comments
	135 °C	275 °F	10N-50°C per hour; ISO 306

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China