

Total PPC 4944WZ Polypropylene, Impact Copolymer

Category : Polymer , Thermoplastic , Polypropylene (PP)

Material Notes:

ATOFINA 4944 polypropylene is a nucleated and controlled rheology impact copolymer. 4944WZ is characterized by improved stiffness and impact resistance, as well as low shrinkage and low warpage. It has been formulated for excellent antistatic properties.

Application ATOFINA 4944 has been developed for high speed injection molding of thin-walled packaging containers and household articles. Information provided provided by Total Petrochemicals. Total Petrochemicals acquired former Fina and Atofina plastics product lines.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Total-PPC-4944WZ-Polypropylene-Impact-Copolymer.php

Physical Properties	Metric	English	Comments
Density	0.905 g/cc	0.0327 lb/in ³	ASTM D1505
Melt Flow	50 g/10 min	50 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	25.5 MPa	3700 psi	ASTM D638
Elongation at Yield	5.0 %	5.0 %	ASTM D638
Flexural Modulus	1.45 GPa	210 ksi	ASTM D 790
Izod Impact, Notched	0.800 J/cm	1.50 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Melting Point	160 - 165 °C	320 - 329 °F	ATOFINA Method
Deflection Temperature at 0.46 MPa (66 psi)	90.0 °C	194 °F	ASTM D648
Vicat Softening Point	150 °C	302 °F	ASTM D1525

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China