

Total PPC 5660 Propylene, Heterophasic Copolymer

Category : Polymer , Thermoplastic , Polypropylene (PP)

Material Notes:

ATOFINA Propylene 5660 is heterophasic copolymer. PPC 5660 is characterized by a medium fluidity offering a combination of ease of processing and good manufactured article properties in applications ranging from household to industrial.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Total-PPC-5660-Propylene-Heterophasic-Copolymer.php

Physical Properties	Metric	English	Comments
Bulk Density	0.525 g/cc	0.0190 lb/in ³	ISO 1183
Density	0.905 g/cc	0.0327 lb/in ³	ISO 1183
Melt Flow	7.0 g/10 min @Load 2.16 kg, Temperature 230 °C	7.0 g/10 min @Load 4.76 lb, Temperature 446 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	85	85	ISO 2039-2
Tensile Strength, Yield	25.0 MPa	3630 psi	ISO 527-2
Elongation at Yield	6.0 %	6.0 %	ISO 527-2
Tensile Modulus	1.30 GPa	189 ksi	ISO 527-2
Flexural Modulus	1.20 GPa	174 ksi	ISO 527-2
Izod Impact, Notched (ISO)	10.0 kJ/m ²	4.76 ft-lb/in ²	ISO 179
	5.50 kJ/m ² @Temperature -20.0 °C	2.62 ft-lb/in ² @Temperature -4.00 °F	ISO 179
Charpy Impact, Notched	1.30 J/cm ²	6.19 ft-lb/in ²	ISO 179
	0.600 J/cm ² @Temperature -20.0 °C	2.86 ft-lb/in ² @Temperature -4.00 °F	ISO 179

Thermal Properties	Metric	English	Comments
Melting Point	165 °C	329 °F	ISO 3146
Deflection Temperature at 0.46 MPa (66 psi)	92.0 °C	198 °F	120°C per hour; ISO 75-2
Deflection Temperature at 1.8 MPa (264 psi)	50.0 °C	122 °F	120°C per hour; ISO 75-2

Thermal Properties	Metric	English	Comments
	135 °C	275 °F	10N-50°C per hour; ISO 306

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China