

Total PPH 10042 Polypropylene, Homopolymer

Category : Polymer , Thermoplastic , Polypropylene (PP)

Material Notes:

ATOFINA Polypropylene PPH 10042 is a nucleated antistatic homopolymer. PPH 10042 is characterized by high fluidity for high speed injection of thin wall articles such as dairy pots and tubs, salad trays and caps and closures. Application PPH 10042 is nucleated and thus has improved rigidity. This coupled with a highly antistatic nature allows for shorter cycle times and easy demolding. Information provided provided by Total Petrochemicals. Total Petrochemicals acquired former Fina and Atofina plastics product lines.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Total-PPH-10042-Polypropylene-Homopolymer.php

Physical Properties	Metric	English	Comments
Bulk Density	0.525 g/cc	0.0190 lb/in ³	ISO 1183
Density	0.905 g/cc	0.0327 lb/in ³	ISO 1183
Melt Flow	35 g/10 min @Load 2.16 kg, Temperature 230 °C	35 g/10 min @Load 4.76 lb, Temperature 446 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	98	98	ISO 2039-2
Tensile Strength, Yield	35.0 MPa	5080 psi	ISO 527-2
Elongation at Yield	8.5 %	8.5 %	ISO 527-2
Tensile Modulus	1.70 GPa	247 ksi	ISO 527-2
Flexural Modulus	1.60 GPa	232 ksi	ISO 527-2
Izod Impact, Notched (ISO)	3.00 kJ/m ²	1.43 ft-lb/in ²	ISO 179
Charpy Impact, Notched	0.350 J/cm ²	1.67 ft-lb/in ²	ISO 179

Thermal Properties	Metric	English	Comments
Melting Point	165 °C	329 °F	ISO 3146
Deflection Temperature at 0.46 MPa (66 psi)	105 °C	221 °F	120°C per hour; ISO 75-2
Deflection Temperature at 1.8 MPa (264 psi)	57.0 °C	135 °F	120°C per hour; ISO 75-2
Vicat Softening Point	90.0 °C	194 °F	50N-50°C per hour; ISO 306
	153 °C	307 °F	10N-50°C per hour; ISO 306

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China