

## Total PPH 9020 Polypropylene, Homopolymer

Category : Polymer , Thermoplastic , Polypropylene (PP)

### Material Notes:

ATOFINA Polypropylene PPH 9020 is a clarified homopolymer. Application ATOFINA Polypropylene PPH 9020 has been designed with a very high stiffness and an outstanding transparency. It is particularly suitable for the injection of syringes and household articles. Information provided provided by Total Petrochemicals. Total Petrochemicals acquired former Fina and Atofina plastics product lines.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Total-PPH-9020-Polypropylene-Homopolymer.php](http://www.lookpolymers.com/polymer_Total-PPH-9020-Polypropylene-Homopolymer.php)

Physical Properties	Metric	English	Comments
Bulk Density	0.525 g/cc	0.0190 lb/in <sup>3</sup>	ISO 1183
Density	0.905 g/cc	0.0327 lb/in <sup>3</sup>	ISO 1183
Melt Flow	25 g/10 min @Load 2.16 kg, Temperature 230 °C	25 g/10 min @Load 4.76 lb, Temperature 446 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	98	98	ISO 2039-2
Tensile Strength, Yield	37.0 MPa	5370 psi	ISO 527-2
Elongation at Yield	8.0 %	8.0 %	ISO 527-2
Tensile Modulus	1.70 GPa	247 ksi	ISO 527-2
Flexural Modulus	1.60 GPa	232 ksi	ISO 527-2
Izod Impact, Notched (ISO)	4.00 kJ/m <sup>2</sup>	1.90 ft-lb/in <sup>2</sup>	ISO 179
Charpy Impact, Notched	0.450 J/cm <sup>2</sup>	2.14 ft-lb/in <sup>2</sup>	ISO 179

Thermal Properties	Metric	English	Comments
Melting Point	165 °C	329 °F	ISO 3146
Deflection Temperature at 0.46 MPa (66 psi)	100 °C	212 °F	120°C per hour; ISO 75-2
Deflection Temperature at 1.8 MPa (264 psi)	55.0 °C	131 °F	120°C per hour; ISO 75-2
Vicat Softening Point	90.0 °C	194 °F	50N-50°C per hour; ISO 306
	153 °C	307 °F	10N-50°C per hour; ISO 306

## **Contact Songhan Plastic Technology Co.,Ltd.**

**Website : [www.lookpolymers.com](http://www.lookpolymers.com)**

**Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)**

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215,Fengxian District, Shanghai City,China**