

Total PPR 7220 Random Copolymer Polypropylene, Injection Molding

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene, Molded

Material Notes:

Total Petrochemicals PPR 7220 is a nucleated random copolymer polypropylene with a melt flow index of 10 g/10 min for the injection molding of articles with high transparency and excellent surface appearance. Polypropylene PPR 7220 is intended for general purpose, household goods, cosmetic caps and closures. Information provided by Total Petrochemicals.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Total-PPR-7220-Random-Copolymer-Polypropylene-Injection-Molding.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.902 g/cc	0.902 g/cc	ISO 1183
Bulk Density	0.525 g/cc	0.0190 lb/in ³	ISO 1183
Melt Flow	10 g/10 min @Load 2.16 kg, Temperature 230 °C	10 g/10 min @Load 4.76 lb, Temperature 446 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	86	86	ISO 2039-2
Tensile Strength, Yield	29.0 MPa	4210 psi	ISO 572-2
Elongation at Yield	10 %	10 %	ISO 572-2
Tensile Modulus	1.30 GPa	189 ksi	ISO 572-2
Flexural Modulus	1.20 GPa	174 ksi	ISO 178
Izod Impact, Notched (ISO)	5.50 kJ/m ²	2.62 ft-lb/in ²	ISO 180
Charpy Impact, Notched	0.700 J/cm ²	3.33 ft-lb/in ²	ISO 179

Thermal Properties	Metric	English	Comments
Melting Point	146 °C	295 °F	ISO 3146
Vicat Softening Point	67.0 °C @Load 5.10 kg	153 °F @Load 11.2 lb	50°C per hour; ISO 306
	130 °C @Load 1.02 kg	266 °F @Load 2.25 lb	50°C per hour; ISO 306

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China