

## Total PS CPDS 827 Flame Retardant Polystyrene

Category : Polymer , Thermoplastic , Polystyrene (PS) , Polystyrene, Flame Retardant

**Material Notes:**

POLYSTYRENE (PS) COMPOUND (CPDS) 827 is a high impact flame retardant polystyrene for use in HGW applications. PS CPDS 827 can be supplied in both natural and colored forms. Main Characteristics: DBDPE and Antimony Trioxide free, Excellent UV stability, Hot Glow Wire rated to 750°C High flow. Applications: Insulated enclosures, Junction boxes. Information provided by Total Petrochemicals.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Total-PS-CPDS-827-Flame-Retardant-Polystyrene.php](http://www.lookpolymers.com/polymer_Total-PS-CPDS-827-Flame-Retardant-Polystyrene.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.04 g/cc	1.04 g/cc	ISO 1183
Water Absorption	<= 0.10 %	<= 0.10 %	ISO 62
Linear Mold Shrinkage	0.0040 - 0.0070 cm/cm	0.0040 - 0.0070 in/in	
Melt Flow	6.0 g/10 min @Load 5.00 kg, Temperature 200 °C	6.0 g/10 min @Load 11.0 lb, Temperature 392 °F	ISO 1133H

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	27.0 MPa	3920 psi	ISO 527-2
Elongation at Break	39 %	39 %	ISO 527-2
Flexural Modulus	2.40 GPa	348 ksi	ISO 178
Izod Impact, Notched (ISO)	7.00 kJ/m <sup>2</sup>	3.33 ft-lb/in <sup>2</sup>	180/1A

Thermal Properties	Metric	English	Comments
Vicat Softening Point	90.0 °C @Load 5.10 kg	194 °F @Load 11.2 lb	50°C per hour; ISO 306B50
Glow Wire Test	750 °C	1380 °F	IEC 695-2-1

Processing Properties	Metric	English	Comments
Melt Temperature	<= 220 °C	<= 428 °F	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215,Fengxian District, Shanghai City,China**