

Toyobo PELPRENE™ P40H Polyester TPE

Category : Polymer , Thermoplastic , Elastomer, TPE , Polyester TPE , Polyester, TP , Polyester Thermoplastic Elastomer

Material Notes:

Features: Polyester TPE Information provided by Toyobo.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Toyobo-PELPRENE-P40H-Polyester-TPE.php

Physical Properties	Metric	English	Comments
Density	1.12 g/cc	0.0405 lb/in ³	ASTM D792
Moisture Absorption at Equilibrium	0.48 %	0.48 %	23°C, 65% RH
Linear Mold Shrinkage	0.0050 cm/cm @Thickness 2.00 mm	0.0050 in/in @Thickness 0.0787 in	
Melt Index of Compound	10 g/10 min @Temperature 190 °C	10 g/10 min @Temperature 374 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	89	89	JIS K6301
Hardness, Shore D	38	38	ASTM D2240
Tensile Strength at Break	21.0 MPa	3050 psi	ASTM D638
Elongation at Break	690 %	690 %	ASTM D638
50% Modulus	0.00640 GPa	0.928 ksi	ASTM D638
Flexural Modulus	0.0510 GPa	7.40 ksi	ASTM D790
Compressive Modulus	0.00450 GPa	0.653 ksi	0.1; ASTM D695
Resilience	78	78	JIS K6301
Izod Impact, Notched	NB	NB	ASTM D256
Tear Strength	98.0 kN/m	559 pli	ASTM D624
Taber Abrasion, mg/1000 Cycles	20	20	ASTM D1044
Compression Set	50 %	50 %	JIS K6301

Thermal Properties	Metric	English	Comments
CTE, linear	170 µm/m-°C	94.4 µin/in-°F	TMA

Thermal Properties	@Temperature 20.0 °C Metric	@Temperature 68.0 °F English	Comments
Melting Point	172 °C	342 °F	By DSC
Vicat Softening Point	120 °C	248 °F	ASTM D1525
Brittleness Temperature	<= -65.0 °C	<= -85.0 °F	JIS K6301
Flammability, UL94	HB	HB	

Electrical Properties	Metric	English	Comments
Volume Resistivity	2.00e+12 ohm-cm	2.00e+12 ohm-cm	ASTM D257
Dielectric Strength	20.0 kV/mm	508 kV/in	JIS K2111

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China