

Toyobo PELPRENE™ P95C Polyester TPE, High Flexibility, High Melting Point

Category : Polymer , Thermoplastic , Elastomer, TPE , Polyester TPE , Polyester, TP , Polyester Thermoplastic Elastomer

Material Notes:

Features: Polyester TPE, High Flexibility, High Melting Point Information provided by Toyobo.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Toyobo-PELPRENE-P95C-Polyester-TPE-High-Flexibility-High-Melting-Point.php

Physical Properties	Metric	English	Comments
Density	1.14 g/cc	0.0412 lb/in ³	ASTM D792
Moisture Absorption at Equilibrium	0.45 %	0.45 %	23°C, 65% RH
Linear Mold Shrinkage	0.0080 cm/cm @Thickness 2.00 mm	0.0080 in/in @Thickness 0.0787 in	
Melt Index of Compound	17 g/10 min @Temperature 230 °C	17 g/10 min @Temperature 446 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	95	95	JIS K6301
Hardness, Shore D	41	41	ASTM D2240
Tensile Strength at Break	27.0 MPa	3920 psi	ASTM D638
Elongation at Break	700 %	700 %	ASTM D638
50% Modulus	0.00830 GPa	1.20 ksi	ASTM D638
Flexural Modulus	0.0740 GPa	10.7 ksi	ASTM D790
Compressive Modulus	0.00760 GPa	1.10 ksi	0.1; ASTM D695
Resilience	75	75	JIS K6301
Izod Impact, Notched	NB	NB	ASTM D256
Tear Strength	108 kN/m	616 pli	ASTM D624
Taber Abrasion, mg/1000 Cycles	17	17	ASTM D1044
Compression Set	52 %	52 %	JIS K6301

Thermal Properties	Metric	English	Comments
CTE, linear	170 µm/m-°C	94.4 µin/in-°F	TMA

Thermal Properties	@Temperature 20.0 °C Metric	@Temperature 68.0 °F English	Comments
Melting Point	213 °C	415 °F	By DSC
Maximum Service Temperature, Air	<= 25.0 °C	<= 77.0 °F	Heat deflection temperature, load unknown; ASTM D648
Vicat Softening Point	162 °C	324 °F	ASTM D1525
Brittleness Temperature	<= -65.0 °C	<= -85.0 °F	JIS K6301
Flammability, UL94	HB	HB	

Electrical Properties	Metric	English	Comments
Volume Resistivity	9.00e+12 ohm-cm	9.00e+12 ohm-cm	ASTM D257
Dielectric Strength	22.0 kV/mm	559 kV/in	JIS K2111

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China