

Tra-Con Tra-Bond 516E01

Category : Polymer , Thermoset

Material Notes:

Information provided by Tra-Con Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Tra-Con-Tra-Bond-516E01.php

Physical Properties	Metric	English	Comments
Viscosity	2200 cP	2200 cP	Mixed (cp #40, 2.5 rpm)

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	79	79	

Thermal Properties	Metric	English	Comments
Glass Transition Temp, Tg	73.0 °C	163 °F	Ultimate Tg

Descriptive Properties	Value	Comments
Color	Dark Blue	Hardener
	Water White	Resin
Mix Ratio, parts by weight	100/47.87	Resin/Hardener

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China