

Tra-Con Tra-Bond 862-13

Category : Polymer , Thermoset

Material Notes:

Information provided by Tra-Con Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Tra-Con-Tra-Bond-862-13.php

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	60	60	2 hrs @ 65°C
Adhesive Bond Strength	11.0 MPa	1600 psi	Lap shear, alum to alum, 2 hrs @ 65°C

Processing Properties	Metric	English	Comments
Cure Time	120 min	2.00 hour	
	@Temperature 65.0 °C	@Temperature 149 °F	

Descriptive Properties	Value	Comments
Color	Black	
Working Life hours	1	Extrudability

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China