

Tra-Con Tra-Bond Ablebond 868-7 Thixotropic Epoxy Adhesive

Category : Polymer , Adhesive , Thermoset , Epoxy , Filled/Reinforced Thermoset

Material Notes:

Ablebond 868-7 flexible epoxy adhesive is a thixotropic version of the 868-series. This nonsag adhesive provides strong bonds to a variety of surfaces. Information provided by Tra-Con Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Tra-Con-Tra-Bond-Ablebond-868-7-Thixotropic-Epoxy-Adhesive.php

Mechanical Properties	Metric	English	Comments
Adhesive Bond Strength	27.6 MPa	4000 psi	Lap shear, alum to alum

Processing Properties	Metric	English	Comments
Cure Time	15.0 min	0.250 hour	
	@Temperature 125 °C	@Temperature 257 °F	
	60.0 min	1.00 hour	
	@Temperature 75.0 °C	@Temperature 167 °F	
Shelf Life	12.0 Month	12.0 Month	
	@Temperature -40.0 °C	@Temperature -40.0 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China