

## Tra-Con Tra-Cast 3012 Clear Epoxy Casting Compound

Category : Polymer , Adhesive , Thermoset , Epoxy

### Material Notes:

TRA-CAST 3012 is a clear, low viscosity epoxy casting compound recommended for industrial embedding and casting applications where its combination of superior properties good clarity, long pot life, near-zero shrinkage, low residual stress, improved flexibility, and excellent impact strength are required. It readily bonds to ceramics, glass, most metals, and many plastics, and it is therefore especially useful for aerospace and electronic applications where its flexibility, consistency and self- sealing properties are needed (i.e. repottable electronic assemblies). Fully cured TRA-CAST 3012 is a clear electrical insulator which is mechanically strong and tougher than comparable silicone gels, and it is further resistant to water, weather, gases and vapors, petroleum products (fuels, solvents and lubricants), mild acids and alkalis, salt solutions and many other organic and inorganic compounds. A vacuum de-airing step for 15 minutes may be required for the best clarity and optical properties. Information provided by Tra-Con Inc.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Tra-Con-Tra-Cast-3012-Clear-Epoxy-Casting-Compound.php](http://www.lookpolymers.com/polymer_Tra-Con-Tra-Cast-3012-Clear-Epoxy-Casting-Compound.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.18 g/cc	1.18 g/cc	Mixed
Solids Content	100 %	100 %	Reactive Solids Content
Viscosity	2100 cP @Temperature 25.0 °C	2100 cP @Temperature 77.0 °F	After mixing

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	79	79	
Elongation at Yield	3.0 %	3.0 %	

Thermal Properties	Metric	English	Comments
CTE, linear	62.0 $\mu\text{m}/\text{m}\cdot\text{°C}$ @Temperature 20.0 °C	34.4 $\mu\text{in}/\text{in}\cdot\text{°F}$ @Temperature 68.0 °F	
Maximum Service Temperature, Air	120 °C	248 °F	
Minimum Service Temperature, Air	-70.0 °C	-94.0 °F	

Optical Properties	Metric	English	Comments
Transmission, Visible	90 %	90 %	clear; thickness not quantified

Electrical Properties	Metric	English	Comments
Volume Resistivity	4.00e+15 ohm-cm	4.00e+15 ohm-cm	

Electrical Properties	Metric	English	Comments
Dielectric Constant	@Frequency 1000 Hz	@Frequency 1000 Hz	
Dielectric Strength	15.4 kV/mm	390 kV/in	
Dissipation Factor	0.020	0.020	
	@Frequency 1000 Hz	@Frequency 1000 Hz	

Processing Properties	Metric	English	Comments
Cure Time	420 min	7.00 hour	2 hrs @ 25°C + 5 hrs @ 55°C
	5760 min	96.0 hour	
	@Temperature 25.0 °C	@Temperature 77.0 °F	
Pot Life	180 min	180 min	

Descriptive Properties	Value	Comments
Color	Clear	
Mix Ratio, parts by weight	100/46	Resin/Hardener
Thixotropic Index	1	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China