

## Trelleborg AEM Eccospheres® W-25 Sodium Borosilicate Glass Microspheres

Category : Ceramic , Glass , Other Engineering Material , Additive/Filler for Polymer

### Material Notes:

Eccospheres® glass microspheres are hollow thin-walled glass microspheres composed of sodium borosilicate glass. To the naked eye they resemble a fine, white, free-flowing powder. However, magnification reveals them to be near perfect spheres. Properties: High temperature resistance, Good density/strength ratios, Clean surface chemistry, Narrow particle size distribution, Low thermal conductivity, Low dielectric constant, Low dissipation factor. The W Series is a special unwashed series perfect for applications such as volume void fillers. Typically referred to as more of a commodity range of microspheres, the W range represents the most economical product offering. All information provided by Trelleborg Emerson & Cuming

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Trelleborg-AEM-Eccospheres-W-25-Sodium-Borosilicate-Glass-Microspheres.php](http://www.lookpolymers.com/polymer_Trelleborg-AEM-Eccospheres-W-25-Sodium-Borosilicate-Glass-Microspheres.php)

Physical Properties	Metric	English	Comments
Pellet Density	0.250 g/cc	0.00903 lb/in <sup>3</sup>	ASTM D2840
Particle Size	50 µm	50 µm	TEC QSD
pH	6.5 - 9.0	6.5 - 9.0	ASTM D4876

Mechanical Properties	Metric	English	Comments
Modulus of Elasticity	62.0 GPa	8990 ksi	
	@Temperature 25.0 °C	@Temperature 77.0 °F	
	62.0 GPa	8990 ksi	
	@Temperature 25.0 °C	@Temperature 77.0 °F	

Thermal Properties	Metric	English	Comments
Thermal Conductivity	0.0730 - 0.125 W/m-K	0.507 - 0.868 BTU-in/hr-ft <sup>2</sup> -°F	

Optical Properties	Metric	English	Comments
Refractive Index	1.448	1.448	
	@Wavelength 1500 nm	@Wavelength 1500 nm	
	1.458	1.458	
	@Wavelength 589.3 nm	@Wavelength 589.3 nm	

Electrical Properties	Metric	English	Comments
Dielectric Constant	1.36 - 1.63	1.36 - 1.63	ASTM D150

Electrical Properties	@Frequency 1e+8 Hz Metric	@Frequency 1e+8 Hz English	Comments
Dissipation Factor	0.00050  @Frequency 1.00e+6 - 8.60e+9 Hz	0.00050  @Frequency 1.00e+6 - 8.60e+9 Hz	ASTM D150

Processing Properties	Metric	English	Comments
Moisture Content	<= 1.0 %	<= 1.0 %	TED QSD

Descriptive Properties	Value	Comments
Floatation (% bulk volume)	95	TEC QSD
Isostatic Collapse Pressure, Min. 80% Survival (psi)	500	ASTM D3102
Packing Factor (min)	58	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China