

Trelleborg B545 High Quality Nitrile Rubber

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE)

Material Notes:

Nitrile rubber or acrylonitrile-butadiene rubber is a copolymer of butadiene and acrylonitrile.PropertiesGood general resistance to oils.Good mechanical properties especially tensile strength, flexing, compression set and impermeability to gases.Moderate aging properties, and good adhesion to metal characteristics.Good adhesion to metal.Moderate resistance to cold.Resistance to Chemicals; good resistance to inorganic chemical products except antioxidant agents and chlorine, and has satisfactory resistance to general hydrocarbons. Being a polar rubber means it is not recommended for use with polar liquids like ketones, ethers and amines. Limited resistance to aromatic hydrocarbons.All information provided by Trelleborg

Order this product through the following link: http://www.lookpolymers.com/polymer_Trelleborg-B545-High-Quality-Nitrile-Rubber.php

| Physical Properties | Metric | English | Comments |
|---------------------|-----------|-----------|----------|
| Specific Gravity | 1.21 g/cc | 1.21 g/cc | |

| Mechanical Properties | Metric | English | Comments |
|-------------------------|---|--|----------|
| Hardness, Shore A | 60 | 60 | |
| Tensile Strength, Yield | 10.0 MPa | 1450 psi | |
| Elongation at Break | 300 % | 300 % | |
| Tear Strength | 25.0 kN/m | 143 pli | |
| Compression Set | 40 % | 40 % | |
| | @Temperature 70.0 °C, Time 79200 sec | @Temperature 158 °F, Time 22.0 hour | |

| Thermal Properties | Metric | English | Comments |
|----------------------------------|----------|----------|----------|
| Maximum Service Temperature, Air | 110 °C | 230 °F | |
| Minimum Service Temperature, Air | -35.0 °C | -31.0 °F | |

| Descriptive Properties | Value | Comments |
|------------------------|-------|----------|
| Color | Black | |

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com Email : sales@lookpolymers.com Tel : +86 021-51131842



Mobile : +86 13061808058 Skype : lookpolymers Address : United North Road 215,Fengxian District, Shanghai City,China