

## Trelleborg B643 High Quality Nitrile Rubber

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE)

**Material Notes:**

Nitrile rubber or acrylonitrile-butadiene rubber is a copolymer of butadiene and acrylonitrile. Properties Good general resistance to oils. Good mechanical properties especially tensile strength, flexing, compression set and impermeability to gases. Moderate aging properties, and good adhesion to metal characteristics. Good adhesion to metal. Moderate resistance to cold. Resistance to Chemicals; good resistance to inorganic chemical products except antioxidant agents and chlorine, and has satisfactory resistance to general hydrocarbons. Being a polar rubber means it is not recommended for use with polar liquids like ketones, ethers and amines. Limited resistance to aromatic hydrocarbons. All information provided by Trelleborg

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Trelleborg-B643-High-Quality-Nitrile-Rubber.php](http://www.lookpolymers.com/polymer_Trelleborg-B643-High-Quality-Nitrile-Rubber.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.17 g/cc	1.17 g/cc	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	65	65	
Tensile Strength, Yield	12.0 MPa	1740 psi	
Elongation at Break	300 %	300 %	
Tear Strength	35.0 kN/m	200 pli	
Compression Set	40 % @Temperature 70.0 °C, Time 79200 sec	40 % @Temperature 158 °F, Time 22.0 hour	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	110 °C	230 °F	
Minimum Service Temperature, Air	-30.0 °C	-22.0 °F	

Descriptive Properties	Value	Comments
Color	Black	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China