

Trelleborg Emerson & Cuming Eccobond® 1309 General Purpose Catalyst

Category : Polymer , Adhesive , Thermoset

Material Notes:

Emerson & Cuming 1309 Eccobond® General Purpose Catalyst Faster curing version of 9. Very fast room temperature curing, low viscosity, general purpose. Short working life. Imparts excellent chemical resistance. Recommended for adhesives and small castings due to high exotherm. Cure Type: Room Temp or Heat

Order this product through the following link:

http://www.lookpolymers.com/polymer_Trelleborg-Emerson-Cuming-Eccobond-1309-General-Purpose-Catalyst.php

Physical Properties	Metric	English	Comments
Density	1.01 g/cc	0.0365 lb/in ³	
Viscosity	75 cP @Temperature 25.0 °C	75 cP @Temperature 77.0 °F	Mixed

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	130 °C	266 °F	
Minimum Service Temperature, Air	-40.0 °C	-40.0 °F	

Processing Properties	Metric	English	Comments
Cure Time	60.0 - 120 min @Temperature 65.0 °C	1.00 - 2.00 hour @Temperature 149 °F	
	480 - 960 min @Temperature 25.0 °C	8.00 - 16.0 hour @Temperature 77.0 °F	
Pot Life	20.0 min @Temperature 25.0 °C	20.0 min @Temperature 77.0 °F	100 grams

Descriptive Properties	Value	Comments
Color	Blue	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China