

Trelleborg Emerson & Cuming Eccobond® 17 M 1 Heat Cure Catalyst

Category : Polymer , Adhesive , Thermoset

Material Notes:

Emerson & Cuming 17 M 1 Eccobond® Heat Cure Catalyst Very high temperature resistance, highest temperature strength, lowest shrink. Non-crystallizing. Long working life. Imparts excellent chemical resistance to cured castings. Recommended for applications requiring the optimum in high temperature performance. Cure Type: Heat

Order this product through the following link:

http://www.lookpolymers.com/polymer_Trelleborg-Emerson-Cuming-Eccobond-17-M-1-Heat-Cure-Catalyst.php

Physical Properties	Metric	English	Comments
Density	1.40 g/cc	0.0506 lb/in ³	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	230 °C	446 °F	
Minimum Service Temperature, Air	-20.0 °C	-4.00 °F	

Processing Properties	Metric	English	Comments
Cure Time	180 min	3.00 hour	
	@Temperature 125 °C	@Temperature 257 °F	
Pot Life	>= 1440 min	>= 1440 min	100 grams
	@Temperature 25.0 °C	@Temperature 77.0 °F	

Descriptive Properties	Value	Comments
Color	Tan	
Viscosity	Slurry at 25°C	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China