

## Trelleborg Emerson & Cuming Eccobond® 23 LV General Purpose Catalyst

Category : Polymer , Adhesive , Thermoset

**Material Notes:**

Emerson & Cuming 23 LV Eccobond® General Purpose Catalyst Excellent low temperature performance properties, excellent thermal shock/cycle and impact resistance. Good hardener for cryogenic applications. Excellent adhesion to glass. Very low viscosity, low exotherm. Light color good for clear castings. Cure Type: Room Temp or Heat

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Trelleborg-Emerson-Cuming-Eccobond-23-LV-General-Purpose-Catalyst.php](http://www.lookpolymers.com/polymer_Trelleborg-Emerson-Cuming-Eccobond-23-LV-General-Purpose-Catalyst.php)

Physical Properties	Metric	English	Comments
Density	1.01 g/cc	0.0365 lb/in <sup>3</sup>	
Viscosity	20 - 30 cP	20 - 30 cP	Mixed
	@Temperature 25.0 °C	@Temperature 77.0 °F	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	105 °C	221 °F	
Minimum Service Temperature, Air	-65.0 °C	-85.0 °F	

Processing Properties	Metric	English	Comments
Cure Time	120 - 240 min	2.00 - 4.00 hour	
	@Temperature 65.0 °C	@Temperature 149 °F	
	960 - 1440 min	16.0 - 24.0 hour	
	@Temperature 25.0 °C	@Temperature 77.0 °F	
Pot Life	60.0 min	60.0 min	100 grams
	@Temperature 25.0 °C	@Temperature 77.0 °F	

Descriptive Properties	Value	Comments
Color	Clear	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China