

Trelleborg Emerson & Cuming Eccobond® 24 LV General Purpose Catalyst

Category : Polymer , Adhesive , Thermoset

Material Notes:

Emerson & Cuming 24 LV Eccobond® General Purpose Catalyst Faster curing, shorter working life version of 23 LV. Recommended for small mass castings due to higher exotherm. Cure Type: Room Temp or Heat

Order this product through the following link:

http://www.lookpolymers.com/polymer_Trelleborg-Emerson-Cuming-Eccobond-24-LV-General-Purpose-Catalyst.php

Physical Properties	Metric	English	Comments
Density	1.01 g/cc	0.0365 lb/in ³	
Viscosity	10 - 25 cP @Temperature 25.0 °C	10 - 25 cP @Temperature 77.0 °F	Mixed

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	105 °C	221 °F	
Minimum Service Temperature, Air	-65.0 °C	-85.0 °F	

Processing Properties	Metric	English	Comments
Cure Time	60.0 - 120 min @Temperature 65.0 °C	1.00 - 2.00 hour @Temperature 149 °F	
	480 - 960 min @Temperature 25.0 °C	8.00 - 16.0 hour @Temperature 77.0 °F	
Pot Life	30.0 min @Temperature 25.0 °C	30.0 min @Temperature 77.0 °F	100 grams

Descriptive Properties	Value	Comments
Color	Clear	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China

