

## Trelleborg Emerson & Cuming Eccobond® 9 General Purpose Catalyst

Category : Polymer , Adhesive , Thermoset

**Material Notes:**

Emerson & Cuming 9 Eccobond® General Purpose Catalyst General purpose, low viscosity. Imparts good physical strength and chemical resistance to cured castings. Recommended for most general purpose applications. Cure Type: Room Temp or Heat

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Trelleborg-Emerson-Cuming-Eccobond-9-General-Purpose-Catalyst.php](http://www.lookpolymers.com/polymer_Trelleborg-Emerson-Cuming-Eccobond-9-General-Purpose-Catalyst.php)

Physical Properties	Metric	English	Comments
Density	1.00 g/cc	0.0361 lb/in <sup>3</sup>	
Viscosity	80 - 105 cP @Temperature 25.0 °C	80 - 105 cP @Temperature 77.0 °F	Mixed

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	130 °C	266 °F	
Minimum Service Temperature, Air	-40.0 °C	-40.0 °F	

Processing Properties	Metric	English	Comments
Cure Time	60.0 - 120 min @Temperature 65.0 °C	1.00 - 2.00 hour @Temperature 149 °F	
	960 - 1440 min @Temperature 25.0 °C	16.0 - 24.0 hour @Temperature 77.0 °F	
Pot Life	45.0 min @Temperature 25.0 °C	45.0 min @Temperature 77.0 °F	100 grams

Descriptive Properties	Value	Comments
Color	Amber	

### Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China

