

Trelleborg Emerson & Cuming Eccobond® B 97 Heat Cure Catalyst

Category : Polymer , Adhesive , Thermoset

Material Notes:

Emerson & Cuming B 97 Eccobond® Heat Cure Catalyst Very high temperature resistance, not as brittle as 17 M 1. Cures from 80°C to 200°C. Excellent chemical resistance. May also be used as an accelerator for 17 M 1. Long working life. Cured castings exhibit excellent retention of properties at elevated temperatures and outstanding chemical resistance. Cure Type: Heat

Order this product through the following link:

http://www.lookpolymers.com/polymer_Trelleborg-Emerson-Cuming-Eccobond-B-97-Heat-Cure-Catalyst.php

Physical Properties	Metric	English	Comments
Density	0.960 g/cc	0.0347 lb/in ³	
Viscosity	4000 - 8000 cP	4000 - 8000 cP	Mixed
	@Temperature 25.0 °C	@Temperature 77.0 °F	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	230 °C	446 °F	
Minimum Service Temperature, Air	-20.0 °C	-4.00 °F	

Processing Properties	Metric	English	Comments
Cure Time	60.0 - 240 min	1.00 - 4.00 hour	
	@Temperature 150 °C	@Temperature 302 °F	
	240 min	4.00 hour	
	@Temperature 60.0 °C	@Temperature 140 °F	
Pot Life	>= 1440 min	>= 1440 min	100 grams
	@Temperature 25.0 °C	@Temperature 77.0 °F	

Descriptive Properties	Value	Comments
Color	Reddish Brown	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China