

Trelleborg Emerson & Cuming Eccobond® D 778 One-Component Fast Cure Epoxy Adhesive

Category : Polymer , Adhesive , Thermoset , Epoxy , Epoxy Adhesive

Material Notes:

Emerson & Cuming D 778 Eccobond® One-Component Fast Cure Epoxy Adhesive High strength, semi-flexible, thixotropic, fast heat curing, epoxy structural adhesive. Good peel strength (20 pli). Recommended for reinforcing riveted or weld bonded metal panels for cabinets, buses, trailers or other sheet metal structures. Cure Type: Heat Bonding Type: Epoxy

Order this product through the following link:

http://www.lookpolymers.com/polymer_Trelleborg-Emerson-Cuming-Eccobond-D-778-One-Component-Fast-Cure-Epoxy-Adhesive.php

Physical Properties	Metric	English	Comments
Density	1.20 g/cc	0.0434 lb/in ³	

Mechanical Properties	Metric	English	Comments
Adhesive Bond Strength	19.3 MPa	2800 psi	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	130 °C	266 °F	
Minimum Service Temperature, Air	-40.0 °C	-40.0 °F	

Processing Properties	Metric	English	Comments
Cure Time	10.0 min	0.167 hour	
	@Temperature 160 °C	@Temperature 320 °F	
	20.0 min	0.333 hour	
	@Temperature 120 °C	@Temperature 248 °F	
	45.0 min	0.750 hour	
	@Temperature 100 °C	@Temperature 212 °F	

Descriptive Properties	Value	Comments
Color	Yellow	
Viscosity	Thixotropic Paste	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China