

## Trelleborg Emerson & Cuming Stycast® 1365-65 Two-Component Epoxy Flexible Encapsulant

Category : Polymer , Adhesive , Thermoset , Epoxy , Epoxy Encapsulant, Unreinforced

### Material Notes:

Emerson & Cuming 1365-65 Stycast® Two-Component Epoxy Flexible Encapsulant Description Excellent adhesion to a variety of substrates. Features Good Chemical Resistance Unfilled Low Viscosity Mix Ratio (by weight) = 100:100 Cure Type: Room Temp or Heat Bonding Type: Epoxy

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Trelleborg-Emerson-Cuming-Stycast-1365-65-Two-Component-Epoxy-Flexible-Encapsulant.php](http://www.lookpolymers.com/polymer_Trelleborg-Emerson-Cuming-Stycast-1365-65-Two-Component-Epoxy-Flexible-Encapsulant.php)

Physical Properties	Metric	English	Comments
Density	1.03 g/cc	0.0372 lb/in <sup>3</sup>	
Viscosity	345 cP @Temperature 25.0 °C	345 cP @Temperature 77.0 °F	Mixed

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	65	65	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	90.0 °C	194 °F	
Minimum Service Temperature, Air	-55.0 °C	-67.0 °F	

Electrical Properties	Metric	English	Comments
Dielectric Constant	4.0 @Frequency 1e+6 Hz	4.0 @Frequency 1e+6 Hz	

Processing Properties	Metric	English	Comments
Cure Time	>= 120 min	>= 2.00 hour	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China