

Trelleborg Emerson & Cuming Stycast® 2760 Two-Component Easy Mix Ratio Encapsulant

Category : Polymer , Adhesive , Thermoset , Epoxy , Epoxy Encapsulant , Unreinforced

Material Notes:

Features and Typical Applications Primarily designed for ease of use in either meter mix or manual dispense operations. These products also offer a wide range of features including heat dissipation, thermal and mechanical shock resistance, and thermal conductivity. Emerson & Cuming 2760 Stycast® Two-Component Easy Mix Ratio Encapsulant Mix Ratio by weight = 100:50 Good Chemical Resistance Thermally Conductive Filled Cure Type: Room Temp or Heat Bonding Type: Epoxy/Polyurethane

Order this product through the following link:

http://www.lookpolymers.com/polymer_Trelleborg-Emerson-Cuming-Stycast-2760-Two-Component-Easy-Mix-Ratio-Encapsulant.php

Physical Properties	Metric	English	Comments
Density	1.55 g/cc	0.0560 lb/in ³	
Viscosity	18000 cP @Temperature 25.0 °C	18000 cP @Temperature 77.0 °F	Mixed

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	80	80	

Thermal Properties	Metric	English	Comments
CTE, linear	122 µm/m-°C @Temperature 20.0 °C	67.8 µin/in-°F @Temperature 68.0 °F	
Thermal Conductivity	0.600 W/m-K	4.16 BTU-in/hr-ft ² -°F	
Maximum Service Temperature, Air	130 °C	266 °F	
Minimum Service Temperature, Air	-40.0 °C	-40.0 °F	

Electrical Properties	Metric	English	Comments
Dielectric Constant	4.0 @Frequency 1e+6 Hz	4.0 @Frequency 1e+6 Hz	
Dielectric Strength	17.7 kV/mm	450 kV/in	

Processing Properties	Metric	English	Comments
Cure Time	>= 120 min	>= 2.00 hour	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China