

Trelleborg Emerson & Cuming Stycast® 933-48 One-Component Epoxy High Service Temp Encapsulant

Category : Polymer , Adhesive , Thermoset , Epoxy , Epoxy Encapsulant , Unreinforced

Material Notes:

Features and Typical Applications Ability to withstand high temperatures, thermal shock, and chemical exposure. These products are designed for heat generating electronic devices which operate in harsh environments. Typical applications include sensors, transformers, power supplies, and rectifiers. Emerson & Cuming 933-48 Stycast® One-Component Epoxy High Service Temp Encapsulant Excellent Chemical Resistance. Cure Type: Heat Bonding Type: Epoxy

Order this product through the following link:

http://www.lookpolymers.com/polymer_Trelleborg-Emerson-Cuming-Stycast-933-48-One-Component-Epoxy-High-Service-Temp-Encapsulant.php

Physical Properties	Metric	English	Comments
Density	1.45 g/cc	0.0524 lb/in ³	
Viscosity	150000 cP @Temperature 25.0 °C	150000 cP @Temperature 77.0 °F	Mixed

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	85	85	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	180 °C	356 °F	
Minimum Service Temperature, Air	-40.0 °C	-40.0 °F	

Processing Properties	Metric	English	Comments
Cure Time	>= 12.0 min	>= 0.200 hour	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China