

## **Trelleborg I644 Antiabrasive SBR Rubber**

Category: Polymer, Thermoset, Rubber or Thermoset Elastomer (TSE)

## **Material Notes:**

Styrene-butadiene Rubber is a co-polymer of styrene and butadiene. Properties the general properties are similar to those of natural rubber, but it is more resistant to aging and temperature, and like natural rubber, these properties can be improved further by careful compounding. Due to its unsaturated molecular structure SBR materials tend to have only moderate resistance to tearing, ozone and general weathering. They do not have the same resilience as natural rubber. Resistance to chemicals; good resistance to many inorganic chemical products. Limited resistance to mineral oils, but is not recommended for use with oxidizing acids and general organic liquids. All information provided by Trelleborg

Order this product through the following link:

http://www.lookpolymers.com/polymer\_Trelleborg-I644-Antiabrasive-SBR-Rubber.php

| Physical Properties | Metric    | English   | Comments |
|---------------------|-----------|-----------|----------|
| Specific Gravity    | 1.13 g/cc | 1.13 g/cc |          |

| Mechanical Properties   | Metric                                  | English                                | Comments                    |
|-------------------------|---|--|-----------------------------|
| Hardness, Shore A       | 60                                      | 60                                     |                             |
| Tensile Strength, Yield | 15.0 MPa                                | 2180 psi                               |                             |
| Elongation at Break     | 400 %                                   | 400 %                                  |                             |
| Tear Strength           | 45.0 kN/m                               | 257 pli                                |                             |
| Abrasion                | 120                                     | 120                                    | mm <sup>3</sup> ; 10 N Load |
| Compression Set         | 35 %                                    | 35 %                                   |                             |
|                         | @Temperature 70.0 °C,<br>Time 79200 sec | @Temperature 158 °F,<br>Time 22.0 hour |                             |

| Thermal Properties               | Metric   | English  | Comments |
|----------------------------------|----------|----------|----------|
| Maximum Service Temperature, Air | 110 °C   | 230 °F   |          |
| Minimum Service Temperature, Air | -40.0 °C | -40.0 °F |          |

## **Contact Songhan Plastic Technology Co.,Ltd.**

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers



Address: United North Road 215, Fengxian District, Shanghai City, China