

## Trelleborg R397 Commercial Natural Rubber Polyisoprene

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE)

**Material Notes:**

All information provided by Trelleborg

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Trelleborg-R397-Commercial-Natural-Rubber-Polyisoprene.php](http://www.lookpolymers.com/polymer_Trelleborg-R397-Commercial-Natural-Rubber-Polyisoprene.php)

Physical Properties	Metric	English	Comments
Specific Gravity	0.950 g/cc	0.950 g/cc	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	35	35	
Tensile Strength, Yield	24.0 MPa	3480 psi	
Elongation at Break	700 %	700 %	
Tear Strength	30.0 kN/m	171 pli	
Abrasion	60	60	mm <sup>3</sup> ; 5 N Load
Compression Set	30 % @Temperature 70.0 °C, Time 79200 sec	30 % @Temperature 158 °F, Time 22.0 hour	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	80.0 °C	176 °F	
Minimum Service Temperature, Air	-40.0 °C	-40.0 °F	

Descriptive Properties	Value	Comments
Color	Red	

### Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China