

Trelleborg R496 Commercial Natural Rubber Polyisoprene

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE)

Material Notes:

All information provided by Trelleborg

Order this product through the following link:

http://www.lookpolymers.com/polymer_Trelleborg-R496-Commercial-Natural-Rubber-Polyisoprene.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.04 g/cc	1.04 g/cc	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	45	45	
Tensile Strength, Yield	16.0 MPa	2320 psi	
Elongation at Break	600 %	600 %	
Tear Strength	30.0 kN/m	171 pli	
Abrasion	80	80	mm ³ ; 5 N Load
Compression Set	30 % @Temperature 70.0 °C, Time 79200 sec	30 % @Temperature 158 °F, Time 22.0 hour	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	85.0 °C	185 °F	
Minimum Service Temperature, Air	-50.0 °C	-58.0 °F	

Descriptive Properties	Value	Comments
Color	Green	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China