

## Trelleborg R504 Commercial Natural Rubber Polyisoprene

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE)

**Material Notes:**

All information provided by Trelleborg

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Trelleborg-R504-Commercial-Natural-Rubber-Polyisoprene.php](http://www.lookpolymers.com/polymer_Trelleborg-R504-Commercial-Natural-Rubber-Polyisoprene.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.01 g/cc	1.01 g/cc	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	40	40	
Tensile Strength, Yield	20.0 MPa	2900 psi	
Elongation at Break	650 %	650 %	
Tear Strength	30.0 kN/m	171 pli	
Abrasion	80	80	mm <sup>3</sup> ; 5 N Load
Compression Set	30 % @Temperature 70.0 °C, Time 79200 sec	30 % @Temperature 158 °F, Time 22.0 hour	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	80.0 °C	176 °F	
Minimum Service Temperature, Air	-40.0 °C	-40.0 °F	

Descriptive Properties	Value	Comments
Color	Red	

### Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China