

Trelleborg R525 Commercial Natural Rubber Polyisoprene

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE)

Material Notes:

All information provided by Trelleborg

Order this product through the following link:

http://www.lookpolymers.com/polymer_Trelleborg-R525-Commercial-Natural-Rubber-Polyisoprene.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.30 g/cc	1.30 g/cc	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	65	65	
Tensile Strength, Yield	8.00 MPa	1160 psi	
Elongation at Break	400 %	400 %	
Tear Strength	20.0 kN/m	114 pli	
Compression Set	38 % @Temperature 70.0 °C, Time 79200 sec	38 % @Temperature 158 °F, Time 22.0 hour	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	70.0 °C	158 °F	
Minimum Service Temperature, Air	-30.0 °C	-22.0 °F	

Descriptive Properties	Value	Comments
Color	Red	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China