

Trelleborg S864 Silicone Rubber

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE) , Silicone , Silicone Rubber

Material Notes:

PropertiesExcellent resistance to heat (dry air), at +200°C continuous and +220°C intermittent. Remains flexible at low temperatures of -70°C. Resistant to ultra-violet light, ozone and weathering. Exhibits low flammability and low smoke toxicity. Good electrical insulation properties. Silicone rubber is physiologically inert, thus making it the preferred choice of the medical, pharmaceutical and food processing industries. Silicones have comparatively low mechanical properties, tensile strength, elongation and tear strength, however they keep constant even at high temperatures but should not be used with high pressure steam. Resistance to chemicals; its resistance to oils and hydrocarbon products is fairly limited and similar to that of Chloroprene rubbers. Reasonable resistance to a whole range of general chemical products, but acids, alkalis, esters and ketones should be avoided. All information provided by Trelleborg

Order this product through the following link:

http://www.lookpolymers.com/polymer_Trelleborg-S864-Silicone-Rubber.php

| Physical Properties | Metric | English | Comments |
|---------------------|-----------|-----------|----------|
| Specific Gravity | 1.48 g/cc | 1.48 g/cc | |

| Mechanical Properties | Metric | English | Comments |
|-------------------------|---|--|----------|
| Hardness, Shore A | 80 | 80 | |
| Tensile Strength, Yield | 7.50 MPa | 1090 psi | |
| Elongation at Break | 250 % | 250 % | |
| Tear Strength | 20.0 kN/m | 114 pli | |
| Compression Set | 45 % @Temperature 70.0 °C, Time 79200 sec | 45 % @Temperature 158 °F, Time 22.0 hour | |

| Thermal Properties | Metric | English | Comments |
|----------------------------------|----------|----------|----------|
| Maximum Service Temperature, Air | 200 °C | 392 °F | |
| Minimum Service Temperature, Air | -70.0 °C | -94.0 °F | |

| Descriptive Properties | Value | Comments |
|------------------------|-------|----------|
| Color | Grey | |

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China