

UBE C (Low-Cis) HIPS (n-DM =0.03 wt %)

Category : Polymer , Thermoplastic , Polystyrene (PS) , Polystyrene, Impact Modified

Material Notes:

Description: UBE high impact polystyrene (HIPS).Information provided by UBE.

Order this product through the following link:

http://www.lookpolymers.com/polymer_UBE-C-Low-Cis-HIPS-n-DM-003-wt-.php

Physical Properties	Metric	English	Comments
Particle Size	2.2 µm	2.2 µm	Rubber Particle Size
Melt Flow	3.5 g/10 min	3.5 g/10 min	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	31.0 MPa	4500 psi	
Tensile Strength, Yield	32.0 MPa	4640 psi	
Elongation at Break	20 %	20 %	
Izod Impact, Notched	0.640 J/cm	1.20 ft-lb/in	

Thermal Properties	Metric	English	Comments
Vicat Softening Point	101 °C	214 °F	

Optical Properties	Metric	English	Comments
Gloss	58 %	58 %	

Descriptive Properties	Value	Comments
MEK/Acetone Insolubles (wt.%)	26.2	
Swelling Index	9.9	

Contact Songhan Plastic Technology Co.,Ltd.Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China