SONGHAN Plastic Technology Co., Ltd.

UBE F222 Polyethylene

Category : Polymer , Thermoplastic , Polyethylene (PE)

Material Notes:

Description: UBE Polyethylene is polymerized at high pressure using a tubular reactor. Production conditions are strictly controlled ensuring the product's superior physical and mechanical properties including transparency and glossiness, and making the material ideal for further processing.Transparency:Superior transparency and glossiness even for applications involving processing of thick objects.Ease of Processing: Excellent fluidity and melt tension characteristics suited to a wide range of molding methods.Inflation molding - can be molded into even thick or wide products with superior bubble stability.Extrusion lamination - can be drawn down even at high speed.Blow molding - can be molded producing a very smooth surface.Injection molding - can be molded even into very thin products.Strength: Good balance in length and breadth with superior tearing strength lengthways.Application: General packingFeatures: Moldability Transparency GlossinessInformation provided by UBE.

Order this product through the following link: http://www.lookpolymers.com/polymer_UBE-F222-Polyethylene.php

Physical Properties	Metric	English	Comments
Density	0.922 g/cc	0.0333 lb/in ³	ASTM D1505
Melt Flow	2.0 g/10 min	2.0 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	54	54	ASTM D2240
Tensile Strength at Break	16.0 MPa	2320 psi	ASTM D638
Elongation at Break	600 %	600 %	ASTM D638
Flexural Strength	15.0 MPa	2180 psi	Olsen; ASTM D747

Thermal Properties	Metric	English	Comments
Vicat Softening Point	94.0 °C	201 °F	ASTM D1525
Brittleness Temperature	<= -75.0 °C	<= -103 °F	ASTM D746

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com Email : sales@lookpolymers.com Tel : +86 021-51131842 Mobile : +86 13061808058 Skype : lookpolymers Address : United North Road 215,Fengxian District, Shanghai City,China