

## **UBE F522N Polyethylene**

Category: Polymer, Thermoplastic, Polyethylene (PE)

## **Material Notes:**

Description: UBE Polyethylene is polymerized at high pressure using a tubular reactor. Production conditions are strictly controlled ensuring the product's superior physical and mechanical properties including transparency and glossiness, and making the material ideal for further processing. Transparency: Superior transparency and glossiness even for applications involving processing of thick objects. Ease of Processing: Excellent fluidity and melt tension characteristics suited to a wide range of molding methods. Inflation molding - can be molded into even thick or wide products with superior bubble stability. Extrusion lamination - can be drawn down even at high speed. Blow molding - can be molded producing a very smooth surface. Injection molding - can be molded even into very thin products. Strength: Good balance in length and breadth with superior tearing strength lengthways. Application: General packing Thin Features: Moldability Information provided by UBE.

Order this product through the following link: http://www.lookpolymers.com/polymer\_UBE-F522N-Polyethylene.php

Physical Properties	Metric	English	Comments
Density	0.922 g/cc	0.0333 lb/in³	ASTM D1505
Melt Flow	5.0 g/10 min	5.0 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	52	52	ASTM D2240
Tensile Strength at Break	14.0 MPa	2030 psi	ASTM D638
Elongation at Break	550 %	550 %	ASTM D638
Flexural Strength	15.0 MPa	2180 psi	Olsen; ASTM D747

Thermal Properties	Metric	English	Comments
Vicat Softening Point	90.0 °C	194 °F	ASTM D1525
Brittleness Temperature	<= -75.0 °C	<= -103 °F	ASTM D746

## **Contact Songhan Plastic Technology Co.,Ltd.**

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058 Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China