

## UBE J5019 Polyethylene

Category : Polymer , Thermoplastic , Polyethylene (PE)

**Material Notes:**

Description: UBE Polyethylene is polymerized at high pressure using a tubular reactor. Production conditions are strictly controlled ensuring the product's superior physical and mechanical properties including transparency and glossiness, and making the material ideal for further processing. Transparency: Superior transparency and glossiness even for applications involving processing of thick objects. Ease of Processing: Excellent fluidity and melt tension characteristics suited to a wide range of molding methods. Inflation molding - can be molded into even thick or wide products with superior bubble stability. Extrusion lamination - can be drawn down even at high speed. Blow molding - can be molded producing a very smooth surface. Injection molding - can be molded even into very thin products. Strength: Good balance in length and breadth with superior tearing strength lengthways. Application: Injection molding Features: Fluidity Information provided by UBE.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_UBE-J5019-Polyethylene.php](http://www.lookpolymers.com/polymer_UBE-J5019-Polyethylene.php)

Physical Properties	Metric	English	Comments
Density	0.919 g/cc	0.0332 lb/in <sup>3</sup>	ASTM D1505
Melt Flow	50 g/10 min	50 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	45	45	ASTM D2240
Tensile Strength at Break	8.00 MPa	1160 psi	ASTM D638
Elongation at Break	250 %	250 %	ASTM D638
Flexural Strength	11.0 MPa	1600 psi	Olsen; ASTM D747

Thermal Properties	Metric	English	Comments
Vicat Softening Point	78.0 °C	172 °F	ASTM D1525
Brittleness Temperature	-30.0 °C	-22.0 °F	ASTM D746

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China