

UBE UBEPOL BR100 Non-Oil Extended Synthetic Rubber Vulcanizate (Cured 35 Minutes at 145°C)

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE)

Material Notes:

Description: UBEPOL BR is UBE's line of polybutadiene rubber products. Information provided by UBE.

Order this product through the following link:

http://www.lookpolymers.com/polymer_UBE-UBEPOL-BR100-Non-Oil-Extended-Synthetic-Rubber-Vulcanizate-Cured-35-Minutes-at-145C.php

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	61	61	ASTM D412
Tensile Strength at Break	18.1 MPa	2630 psi	ASTM D412
Elongation at Break	530 %	530 %	ASTM D412
100% Modulus	0.00200 GPa	0.290 ksi	ASTM D412
200% Modulus	0.00520 GPa	0.754 ksi	ASTM D412
300% Modulus	0.00920 GPa	1.33 ksi	ASTM D412
Tear Strength	41.0 kN/m	234 pli	ASTM D2240

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China