

UBE UBEPOL BR130B Non-Oil Extended Synthetic Rubber Vulcanizate (Cured 35 Minutes at 145°C)

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE)

Material Notes:

Description: UBEPOL BR is UBE's line of polybutadiene rubber products. Information provided by UBE.

Order this product through the following link:

http://www.lookpolymers.com/polymer_UBE-UBEPOL-BR130B-Non-Oil-Extended-Synthetic-Rubber-Vulcanizate-Cured-35-Minutes-at-145C.php

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	56	56	ASTM D412
Tensile Strength at Break	14.8 MPa	2150 psi	ASTM D412
Elongation at Break	470 %	470 %	ASTM D412
100% Modulus	0.00180 GPa	0.261 ksi	ASTM D412
200% Modulus	0.00430 GPa	0.624 ksi	ASTM D412
300% Modulus	0.00760 GPa	1.10 ksi	ASTM D412
Tear Strength	32.0 kN/m	183 pli	ASTM D2240

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China