

## UBE UBEPOL BR150B Non-Oil Extended Synthetic Rubber Vulcanizate (Cured 35 Minutes at 145°C)

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE)

### Material Notes:

Description: UBEPOL BR is UBE's line of polybutadiene rubber products. Information provided by UBE.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_UBE-UBEPOL-BR150B-Non-Oil-Extended-Synthetic-Rubber-Vulcanizate-Cured-35-Minutes-at-145C.php](http://www.lookpolymers.com/polymer_UBE-UBEPOL-BR150B-Non-Oil-Extended-Synthetic-Rubber-Vulcanizate-Cured-35-Minutes-at-145C.php)

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	59	59	ASTM D412
Tensile Strength at Break	16.3 MPa	2360 psi	ASTM D412
Elongation at Break	470 %	470 %	ASTM D412
100% Modulus	0.00200 GPa	0.290 ksi	ASTM D412
200% Modulus	0.00510 GPa	0.740 ksi	ASTM D412
300% Modulus	0.00900 GPa	1.31 ksi	ASTM D412
Tear Strength	39.0 kN/m	223 pli	ASTM D2240

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China