

UBE UBEPOL BR340L Non-Oil Extended Synthetic Rubber Vulcanizate (Cured 50 Minutes at 145°C)

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE)

Material Notes:

Description: UBEPOL BR is UBE's line of polybutadiene rubber products. Information provided by UBE.

Order this product through the following link:

http://www.lookpolymers.com/polymer_UBE-UBEPOL-BR340L-Non-Oil-Extended-Synthetic-Rubber-Vulcanizate-Cured-50-Minutes-at-145C.php

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	62	62	ASTM D412
Tensile Strength at Break	17.9 MPa	2600 psi	ASTM D412
Elongation at Break	510 %	510 %	ASTM D412
100% Modulus	0.00220 GPa	0.319 ksi	ASTM D412
200% Modulus	0.00530 GPa	0.769 ksi	ASTM D412
300% Modulus	0.00970 GPa	1.41 ksi	ASTM D412
Rebound	56 %	56 %	BS.903,PART22
Tear Strength	45.0 kN/m	257 pli	ASTM D624
Abrasion	102	102	Lombourn Abrasion Index (Iwamoto Seisakusyo, Japan); UBE Method
	191	191	Pico Abrasion Index; ASTM D2228
Compression Set	16 %	16 %	Method B, 70°C, 72hrs; ASTM D395

Descriptive Properties	Value	Comments
Cut Generation De Mattia Flexing Machine	Min 300,000 times	ASTM D430
Cut Growth (2mm-->15mm) De Mattia Flexing Machine	3000 times	ASTM D313
Goodrich Flex, 0.175" Stroke, 55lb, 100°C, P.S.	10%	ASTM D623 (34°C change in temperature)
Wet Skid Resistance on Safety-Walk	18	UBE Method (British Portable Skid Resistance Tester)

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China